

STEEL			
D [mm]	IR[mm]	K	V[mm]
0.5	0.7	0.4717	4
0.6	1	0.3917	6
0.8	1	0.4498	6
1.0	1	0.4566	6
1.2	1.3	0.4414	8
1.5	1.3	0.4507	8
2.0	2	0.4572	12
2.5	2.7	0.4555	16
3.0	3.3	0.4466	20
4.0	4	0.4423	25
5.0	5.8	0.4448	35
6.0	8	0.4271	50
8.0	16	0.4032	100
10.0	16	0.3738	100
12.0	16	0.4271	100

STAINLESS STEEL			
D [mm]	IR[mm]	K	V[mm]
0.5	0.7	0.2832	4
0.6	1	0.2029	6
0.8	1	0.2906	6
1.0	1	0.3356	6
1.2	1.3	0.3151	8
1.5	1.3	0.3522	8
2.0	2	0.335	12
2.5	2.7	0.3313	16
3.0	3.3	0.3201	20
4.0	4	0.3191	25
5.0	5.8	0.3159	35
6.0	8	0.2398	50
8.0	16	0.123	100
10.0	16	0.1855	100
12.0	16	0.2398	100

AL			
D [mm]	IR[mm]	K	V[mm]
0.5	0.7	0.5506	4
0.6	1	0.5679	6
0.8	1	0.523	6
1.0	1	0.4961	6
1.2	1.3	0.5008	8
1.5	1.3	0.4787	8
2.0	2	0.4961	12
2.5	2.7	0.507	16
3.0	3.3	0.5051	20
4.0	4	0.4894	25
5.0	5.8	0.5125	35
6.0	8	0.5241	50
8.0	16	0.5774	100
10.0	16	0.5499	100
12.0	16	0.5241	100

D - дебелина на материала

IR - вътрешен радиус на огъване

K - к-фактор

V - размер на призмата









